

AVF Concrete Sealer

Transparent two component sealer. (Line 315)

Description

Technical Data

AVF Concrete Sealer is a transparent non-saponifiable sealer. AVF Concrete Sealer will prevent absorption of finishing coats into substrates.

.....

Product Information

AVF Concrete Sealer

	Avi Concrete Sedier
Vehicle Type	Epoxy polyamide
Pigment Type	-
Solids by Volume	21%
Theoretical Coverage	34 m²/US Gallon @25µ DFT
Depending on surface texture	•
and porosity	
Recommended Film Thickness	
Wet	150µm
Dry	25µm
Dry Time @ 25°C	
To Touch	2 Hours
To Handle	16 Hours
To Recoat	After 16 Hours, within 3 Days
Dries By	Reactive drying
Flash Point	<21°C
Gloss	Gloss
Thin with	Do not thin
Clean up Thinner	Thinner #316 or Thinner #290
Mixing ratio	84/16 by volume 83.7/16.3 by weight

Recommended For

To be applied on concrete and untreated asbestos cement. Note: Do not apply at a relative humidity of over 80%.

Color

Clear.

PO BOX 3944 T Asteroïdenweg z/n F Willemstad, Curaçao E

T +5999 736 5866 F +5999 736 5044 E info@avfpaint.com

WWW.AVFPAINT.COM



Applicable by

Brush, roller or airless spray.

Packing ¼ US Gallon (0.945 Liters). 1 US Gallon (3.785 Liters).

Clean up

Clean brushes and rollers with Thinner #316 or Thinner #290 after use.

Safety Information

Use with adequate ventilation. Avoid contact with eyes and repeated contact with skin. Wear eye protection and gloves during application.

First Aid

If you experience difficulty in breathing, leave area immediately. In case of eye contact, flush with plenty of water. In case of ingestion, do not induce vomiting. Get medical help immediately.

Remark

Surface must be clean, free of loose paint, chalk, grease and dust. Patch damaged areas and chalk open joints. If any areas are peeled, cracked or blistered, the condition causing this must be corrected for successful painting. Metal parts such as nail heads, should be wiped clean and primed with the appropriate metal primer. If mildew is present remove all traces with a solution of Ammonia. CAUTION: use protective clothing and work goggles when applying Ammonia solution. WARNING! Scraping or sanding of old paint may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS. PREGNANT WOMEN SHOULD AVOID EXPOSURE.

Limitation of liability: The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Pintuco Curacao B.V., whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. Pintuco Curacao B.V. has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Pintuco Curacao B.V. does therefore not accept any liability arising from loss or injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise). The data contained herein are liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues and it is the user's responsibility to ensure that this sheet is the current prior to using the product. The English text of this document shall prevail over any translation thereof.

Version: May 2017

PO BOX 3944 Asteroïdenweg z/n Willemstad, Curaçao T +5999 736 5866 F +5999 736 5044 E info@avfpaint.com

WWW.AVFPAINT.COM