

Comocoat

Cement containing roof paint for light metals and aluminum sheets.
(Line 105)

Description

Comocoat is a cementitious roof paint based on a modified alkyd. Comocoat is especially formulated for use on zinc plated steel, light metals and aluminum sheets and galvanized metal. Comocoat will not become brittle and flake.

.....

Product Information

Technical Data

Comocoat

| | |
|--|---|
| Vehicle Type | Modified alkyd |
| Pigment Type | Titanium Dioxide |
| Solids by Volume | 46% |
| Theoretical Coverage | 34 m ² /US Gallon @ 35µm DFT |
| <i>Depending on surface texture and porosity</i> | |
| Recommended Film Thickness | |
| Wet | 50µm |
| Dry | 35µm |
| Dry Time @ 25°C | |
| To Touch | 6 Hours |
| To Handle | 16 Hours |
| To Recoat | 36 Hours |
| Dries By | Evaporation / Oxidation |
| Flash Point | - |
| Gloss | Semi flat |
| Thin with | Thinner #902 (max 5% by weight) |
| Clean up Thinner | Thinner #902 |
| Weight Per Gallon | 5.49-5.87kg/gallon |

Recommended For

Comocoat is excellent for painting of galvanized roof sheets light metals and aluminum sheets. Comocoat should be applied directly on metal sheets to obtain maximum adhesion.

Color

Color card.

Applicable by

Brush or roller.

Packing

1 US Gallon (3.785 Liters).

Clean up

Clean brushes and rollers thinner #902 after use.

Safety Information

Use with adequate ventilation. Avoid contact with eyes and repeated contact with skin. Wear eye protection and gloves during application.

First Aid

If you experience difficulty in breathing, leave area immediately. In case of eye contact, flush with plenty of water. In case of ingestion, do not induce vomiting. Get medical help immediately.

Remark

Surface must be clean, free of loose paint, chalk, grease and dust. Patch damaged areas and chalk open joints. If any areas are peeled, cracked or blistered, the condition causing this must be corrected for successful painting. Metal parts such as nail heads, should be wiped clean and primed with the appropriate metal primer. New plasterwork (PH greater than 10) has to cure properly and should be primed with one (1) or two (2) coats of AVF Wall Sealer. If mildew is present remove all traces with a solution of Ammonia. CAUTION: use protective clothing and work goggles when applying Ammonia solution. WARNING! Scraping or sanding of old paint may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS. PREGNANT WOMEN SHOULD AVOID EXPOSURE. New plaster must be allowed to cure (30-60 days).

.....
Limitation of liability: The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Pintuco Curacao B.V., whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. Pintuco Curacao B.V. has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Pintuco Curacao B.V. does therefore not accept any liability arising from loss or injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise). The data contained herein are liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues and it is the user's responsibility to ensure that this sheet is the current prior to using the product. The English text of this document shall prevail over any translation thereof.

Version: May 2017