

## AVF Floor Flex (Floor & Patio Paint)

Specially formulated for patios, sidewalks, tennis courts etc.  
(Line 206)

### Description

AVF Floor Flex is specially formulated to protect and beautify interior and exterior masonry floors, masonry patios, sidewalks, steps, tennis courts, asphalt playing courts etc. This 100% acrylic paint is highly resistant to mildew, scuffing due to traffic, washing and house hold chemicals. Floor Flex contains a non-skid additive to prevent slips.

---

### Product Information

#### Technical Data

#### AVF Floor Flex

|  |   |
|--|---|
| Vehicle Type                                     | 100% Acrylic                            |
| Pigment Type                                     | Titanium Dioxide                        |
| Solids by Volume                                 | 52%                                     |
| Theoretical Coverage                             | 30 m <sup>2</sup> /US Gallon @ 35µm DFT |
| <i>Depending on surface texture and porosity</i> |   |
| Recommended Film Thickness                       |   |
| Wet  | 100µm                                   |
| Dry  | 35µm                                    |
| Dry Time @ 25°C                                  |   |
| To Touch   | 1 Hours                                 |
| To Handle  | 4 Hours                                 |
| To Recoat  | 9 hours                                 |
| Dries By   | Evaporation / Coalescence               |
| Flash Point                                      | -                                       |
| Gloss  | Flat                                    |
| Thin with  | Water (max 5% by volume)                |
| Clean up Thinner                                 | Water                                   |
| Weight Per Gallon                                | 4.92 kg/gallon                          |

### Recommended For

Interior and exterior masonry floors, porches, patios and sidewalks. Tennis courts, asphalt playing courts. Note: Not recommended for areas subject to hot tire pickup.

### Color

White, bright yellow, pearl grey, tennis green, patio red.

### Applicable by

Brush or roller.

### Packing

1 US Gallon (3.785 Liters).

5 US Gallon (18.93 Liters).

### Clean up

Clean brushes and rollers with clean water after use.

### Safety Information

Use with adequate ventilation. Avoid contact with eyes and repeated contact with skin.

Wear eye protection and gloves during application.

### First Aid

If you experience difficulty in breathing, leave area immediately. In case of eye contact, flush with plenty of water. In case of ingestion, do not induce vomiting. Get medical help immediately.

### Remark

Surface must be clean, free of loose paint, chalk, grease and dust. Patch damaged areas and chalk open joints. If any areas are peeled, cracked or blistered, the condition causing this must be corrected for successful painting.

**Poured Concrete (new):** Surfaces must be clean, dry, sound and offer sufficient profile to achieve adequate adhesion. Minimum substrate cure is 28 days at 24°C. Remove all form release agents, curing compounds, salts, efflorescence, and other foreign material by sandblasting, mechanical scarification, or suitable chemical means, such as muriatic acid etch. Rinse thoroughly to achieve a final pH between 6.0 and 10.0. Allow to dry thoroughly prior to coating.

**Poured Concrete (old):** Surface preparation is done in much the same manner as new concrete. However, if the concrete is contaminated with oils, grease, chemicals, etc., they must be removed by cleaning with a strong detergent. Form release agents, hardeners, etc. must be removed by sandblasting, mechanical scarification, or suitable chemical means. If surface deterioration presents and unacceptably rough surface, patch and resurface damaged concrete.

**WARNING!** Scraping or sanding of old paint may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS. PREGNANT WOMEN SHOULD AVOID EXPOSURE.

.....  
**Limitation of liability:** The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Pintuco Curacao B.V., whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. Pintuco Curacao B.V. has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Pintuco Curacao B.V. does therefore not accept any liability arising from loss or injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise). The data contained herein are liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues and it is the user's responsibility to ensure that this sheet is the current prior to using the product. The English text of this document shall prevail over any translation thereof.

Version: May 2017

PO BOX 3944

Asteroidenweg z/n

Willemstad, Curaçao

T +5999 736 5866

F +5999 736 5044

E info@avfpaint.com

[WWW.AVFPAIN.COM](http://WWW.AVFPAIN.COM)