

## Hechtgrond N° 8425

Adhesive coat for porous materials.  
(Line 210)

### Description

Hechtgrond N° 8425 is a Modified polyvinyl based emulsion used as an adhesion coat for porous materials. Hechtgrond N° 8425 provides an excellent adhesion between old concrete and new plaster.

.....

### Product Information

<u>Technical Data</u>	<u>Hechtgrond N° 8425</u>
Vehicle Type	Modified polyvinyl
Pigment Type	-
Solids by Volume	47%
Theoretical Coverage	30 m <sup>2</sup> /US Gallon
<i>Depending on surface texture and porosity</i>	
Recommended Film Thickness	
Wet	Impregnating
Dry	Impregnating
Dry Time @ 25 °C	
To Touch	½ Hour
To Handle	2 Hours
To Recoat	2 hours
Dries By	Evaporation
Flash Point	-
Gloss	-
Thin with	Water (max 20%-30% by volume)
Clean up Thinner	Water
Weight Per Gallon	4.01 kg/gallon

### Recommended For

Suitable for bonding new plaster on to old plaster. This product is intended for use by professional contractors.

### Color

Milky white.

### **Applicable by**

Brush, roller or airless spray.

### **Packing**

1 US Gallon (3.785 Liters)

### **Clean up**

Clean brushes and rollers with clean water after use. Spray equipment should be cleaned with water and given a final rinse with White Spirit.

### **Safety Information**

Use with adequate ventilation. Avoid contact with eyes and repeated contact with skin. Wear eye protection and gloves during application.

### **First Aid**

If you experience difficulty in breathing, leave area immediately. In case of eye contact, flush with plenty of water. In case of ingestion, do not induce vomiting. Get medical help immediately.

### **Remark**

Surface must be clean, free of loose paint, chalk, grease and dust. Patch damaged areas and chalk open joints. If any areas are peeled, cracked or blistered, the condition causing this must be corrected for successful painting. Metal parts such as nail heads, should be wiped clean and primed with the appropriate metal primer. New plasterwork (PH greater than 10) has to cure properly and should be primed with one (1) or two (2) coats of AVF Wall Sealer. If mildew is present remove all traces with a solution of Ammonia. CAUTION: use protective clothing and work goggles when applying Ammonia solution. WARNING! Scraping or sanding of old paint may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS. PREGNANT WOMEN SHOULD AVOID EXPOSURE. New plaster must be allowed to cure (30-60 days).

.....  
**Limitation of liability:** The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All or recommendations suggestions relating to the use of the products made by Pintuco Curacao B.V., whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. Pintuco Curacao B.V. has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Pintuco Curacao B.V. does therefore not accept any liability arising from loss or injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise). The data contained herein are liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues and it is the user's responsibility to ensure that this sheet is the current prior to using the product. The English text of this document shall prevail over any translation thereof.

Version: May 2017