

Pehalin® Edelhout HG (Stain & Varnish)

Pehalin® Edelhout HG (Stain & Varnish) adds rich color to timber and simultaneously preserves the stain by protecting it with a highly durable clear finish.

(Line 113)

Description

Pehalin® Edelhout HG is a premium quality, high gloss solvent based interior/exterior stain & varnish, formulated to penetrate, protect and beautify wood decking, fencing, siding and furniture. Pehalin® Edelhout HG contains U.V. absorbers for long lasting performance. Pehalin® Edelhout HG masks the grain of the wood and enhances the natural texture.

.....

Product Information

Technical Data

Pehalin® Edelhout HG

Vehicle Type	Modified alkyd
Pigment Type	31%
Solids by Volume	60 m ² /US Gallon 20µm DFT
Theoretical Coverage	
<i>Depending on surface texture and porosity</i>	
Recommended Film Thickness	50µm
Wet	20µm
Dry	
Dry Time @ 25° C	5 Hours
To Touch	7 Hours
To Handle	
To Recoat	24 Hours
Dries By	Evaporation / Oxidation
Flash Point	-
Gloss	Gloss
Thin with	Thinner#902
Clean up Thinner	Thinner #902
Weight Per Gallon	3.52 kg/gallon

Recommended For

Wood decking, fencing, siding and furniture.

Color

Color card.

Applicable by

Brush, roller or airless spray.

Packing

1/4 US Gallon (0.945 Liters).

1 US Gallon (3.785 Liters).

Clean up

Clean brushes and rollers with thinner #902 after use.

Safety Information

Use with adequate ventilation. Avoid contact with eyes and repeated contact with skin. Wear eye protection and gloves during application.

First Aid

If you experience difficulty in breathing, leave area immediately. In case of eye contact, flush with plenty of water. In case of ingestion, do not induce vomiting. Get medical help immediately.

Remark

Surface must be clean, dry and free of dirt, mildew, oil or grease. Remove all contaminants and residue by washing with a multi-purpose cleaner. If mildew is evident it must be removed by scrubbing, or it will continue to grow through fresh coating. If mildew is widespread, the use of power wash spray equipment is suggested. Previously painted or varnished wood can be restored by sanding or by using paint remover. All traces of paint remover should be washed off with water. For best results remove previous coating completely. Wood glaze has to be eliminated to allow proper penetration and adhesion of varnish. Weathered wood must be sanded until a sound surface is obtained. **WARNING! Scraping or sanding of old paint may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS. PREGNANT WOMEN SHOULD AVOID EXPOSURE.**

.....
Limitation of liability: The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Pintuco Curacao B.V., whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. Pintuco Curacao B.V. has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Pintuco Curacao B.V. does therefore not accept any liability arising from loss or injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise). The data contained herein are liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues and it is the user's responsibility to ensure that this sheet is the current prior to using the product. The English text of this document shall prevail over any translation thereof.

Version: May 2017