

AVF Revoque Plastico

Substitute for traditional plaster
(Line 605)

Description

AVF Revoque Plastico is a coarse-grained plastic putty, with high filling power, to be used as a substitute for traditional plaster in interior and exterior surfaces. AVF Revoque Plastico guarantees excellent adhesion, coverage and durability of the finish coat. *This product conforms to LEED IEQc 4.2 requirements; Low-Emitting Materials—Paints and Coatings.*

.....

Product Information

Technical Data

AVF Revoque Plastico

Vehicle Type	Acrylic Copolymer
Pigment Type	Titanium Dioxide
Solids by Volume	-
Theoretical Coverage	3.3-3.7 kg/m ² @ 2 - 3 mm DFT
<i>Depending on surface texture and porosity</i>	-
Recommended Film Thickness	-
Wet	
Dry	4 Hours
Dry Time @ 25° C	6 Hours
To Touch	
To Handle	
To Recoat	24 hours
Dries By	Evaporation
Flash Point	-
Gloss	-
Thin with	Water
Clean up Thinner	Water
Weight Per Gallon	7.42 - 7.52 kg/gallon

Recommended For

Recommended for replacing traditional plaster in interior and exterior surfaces. AVF Revoque Plastico can be applied to a thickness of up to 3 cm in successive layers without cracking and without having to add cement or plaster. AVF Revoque Plastico is perfectly suited to create a seamless surface between slabs of poured concrete, asbestos cement slabs, structural bricks, concrete blocks, or masonry in general. AVF

Revoque Plastico promotes adhesion of decorative and textured paints in interior and exterior surfaces.

Color

White.

Applicable by

Trowel.

Packing

Bucket 30 kg

Clean up

Clean brushes and rollers with clean water after use.

Safety Information

Use with adequate ventilation. Avoid contact with eyes and repeated contact with skin. Wear eye protection and gloves during application.

First Aid

If you experience difficulty in breathing, leave area immediately. In case of eye contact, flush with plenty of water. In case of ingestion, do not induce vomiting. Get medical help immediately.

Remark

Surface must be clean, free of loose paint, chalk, grease and dust. Patch damaged areas and chalk open joints. If any areas are peeled, cracked or blistered, the condition causing this must be corrected for successful painting. Metal parts such as nail heads, should be wiped clean and primed with the appropriate metal primer. New plasterwork (PH greater than 10) has to cure properly and should be primed with one (1) or two (2) coats of AVF Wall Sealer. If mildew is present remove all traces with a solution of Ammonia. CAUTION: use protective clothing and work goggles when applying Ammonia solution. WARNING! Scraping or sanding of old paint may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS. PREGNANT WOMEN SHOULD AVOID EXPOSURE. New concrete must be allowed to cure (30-60 days).

.....
Limitation of liability: The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Pintuco Curacao B.V., whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. Pintuco Curacao B.V. has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Pintuco Curacao B.V. does therefore not accept any liability arising from loss or injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise). The data contained herein are liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues and it is the user's responsibility to ensure that this sheet is the current prior to using the product. The English text of this document shall prevail over any translation thereof.

Version: May 2017