

Magna® Acrylcoat

100% Acrylic paint for exterior use with maximum weather resistant properties.
(Line 211)

Description

Magna® Acryl coat is 100% acrylic latex paint for exterior use. Magna® Acryl coat has a matte sheen, mildew resistant finish, perfect for extreme climatic conditions. Magna® Acryl coat offers improved hiding for greater coverage and excellent color retention*, the ultimate in durability. Magna® Acryl coat is very easily applied with brush or roller and is ideally suitable for the decoration and protection of air-dried walls, fiber building boards, brick, masonry, stucco and cinder block. LEAD FREE product.

Product Information

Technical Data

Magna® Acrylcoat

Vehicle Type	100% Acrylic
Pigment Type	Titanium Dioxide
Solids by Volume	41%
Theoretical Coverage	43 m ² /US Gallon @ 35µm DFT
<i>Depending on surface texture and porosity</i>	47 m ² /US Gallon @ 32µm DFT
Recommended Film Thickness	
Wet	72/85µm
Dry	32/35µm
Dry Time @ 25°C	
To Touch	4 Hours
To Handle	6 Hours
To Recoat	12 hours
Dries By	Evaporation, coalescence
Flash Point	-
Gloss	Matte
Thin with	Water
	(max 3% by volume for brush or roller, max 5% by volume for airless spray)
Clean up Thinner	Water
Weight Per Gallon	5.49 kg/gallon

Recommended For

Exterior and interior use on primed or previously painted masonry such as stucco, cement block construction, poured and precast concrete.

Color

Color card shades*, AVF Paints color system and Special Colors upon request.

**Excellent color retention guaranteed only on color card shades and derivatives thereof.*

Applicable by

Brush, roller or airless spray.

Packing

1 US Gallon (3.785 Liters).

5 US Gallon (18.93 Liters).

Clean up

Clean brushes and rollers with clean water after use.

Safety Information

Use with adequate ventilation. Avoid contact with eyes and repeated contact with skin. Wear eye protection and gloves during application.

First Aid

If you experience difficulty in breathing, leave area immediately. In case of eye contact, flush with plenty of water. In case of ingestion, do not induce vomiting. Get medical help immediately.

Remark

Surface must be clean, free of loose paint, chalk, grease and dust. Patch damaged areas and chalk open joints. If any areas are peeled, cracked or blistered, the condition causing this must be corrected for successful painting. Metal parts such as nail heads, should be wiped clean and primed with the appropriate metal primer. New plasterwork (PH greater than 10) has to cure properly and should be primed with one (1) or two (2) coats of AVF Wall Sealer. If mildew is present remove all traces with a solution of Ammonia. CAUTION: use protective clothing and work goggles when applying Ammonia solution. WARNING! Scraping or sanding of old paint may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS. PREGNANT WOMEN SHOULD AVOID EXPOSURE. New plaster must be allowed to cure (30-60 days).

.....
Limitation of liability: The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Pintuco Curacao B.V., whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. Pintuco Curacao B.V. has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Pintuco Curacao B.V. does therefore not accept any liability arising from loss or injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise). The data contained herein are liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues and it is the user's responsibility to ensure that this sheet is the current prior to using the product. The English text of this document shall prevail over any translation thereof.