

Sellamur®

Waterproofing for walls with rising humidity.

(Line 215)

Description

Sellamur® is a high-performance waterproofing coating that prevents the appearance of efflorescence, fungus and algae. In addition, it seals the substrate to inhibit the passage of moisture by capillarity or negative pressure, Sellamur® is a white, high-coverage decorative finish that can be covered with other decorative and protective products from AVF Paints.

Product Information

Technical Data

Sellamur®

Vehicle Type	Acrylic Copolymers
Pigment Type	Titanium Dioxide
Solids by Volume	37%
Theoretical Coverage	39 m ² /US Gallon @ 35µm DFT
<i>Depending on surface texture and porosity</i>	
Recommended Film Thickness	
Wet	95µm
Dry	35µm
Dry Time @ 25°C	
To Touch	1 Hour
To Handle	1 Hours
To Recoat	4 hours
Dries By	Evaporation / Coalescence
Flash Point	-
Gloss	Flat
Thin with	Do not Dilute
Clean up Thinner	Water
Weight Per Gallon	5.00 kg/gallon

Recommended For

Formulated for waterproofing all interior and exterior masonry, cinder, concrete, stucco and brick retaining walls above or below grade. Also ideal to prevent the appearance of mold, algae and fungi on substrates.

Color

White

Rev.: April/2024

Applicable by

Brush or roller.

Packing

1 US Gallon (3.785 Liters).

5 US Gallon (18.93 Liters).

Clean up

Clean brushes and rollers with clean water after use.

Safety Information

Use with adequate ventilation. Avoid contact with eyes and repeated contact with skin. Wear eye protection and gloves during application.

First Aid

If you experience difficulty in breathing, leave area immediately. In case of eye contact, flush with plenty of water. In case of ingestion, do not induce vomiting. Get medical help immediately.

Remark

Surface must be clean, free of loose paint, chalk, grease and dust. Patch damaged areas and chalk open joints. If any areas are peeled, cracked or blistered, the condition causing this must be corrected for successful painting. Metal parts such as nail heads, should be wiped clean and primed with the appropriate metal primer. New plasterwork (PH greater than 10) has to cure properly and should be primed with one (1) or two (2) coats of AVF Wall Sealer. If mildew is present remove all traces with a solution of Ammonia. CAUTION: use protective clothing and work goggles when applying Ammonia solution. WARNING! Scraping or sanding of old paint may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS. PREGNANT WOMEN SHOULD AVOID EXPOSURE. New plaster must be allowed to cure (30-60 days).

.....
Limitation of liability: The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Pintuco Curacao B.V., whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. Pintuco Curacao B.V. has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Pintuco Curacao B.V. does therefore not accept any liability arising from loss or injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise). The data contained herein are liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues and it is the user's responsibility to ensure that this sheet is the current prior to using the product. The English text of this document shall prevail over any translation thereof.